

Technical Data Sheet

3M™ Scotch-Weld™ Epoxy Adhesive DP110 Translucent

Product Description

3M™ Scotch-Weld™ Epoxy Adhesive DP110 Translucent is a two-part epoxy adhesive which combines a fast cure with flexibility.


Product Features

- Controlled flow
- 20 minute handling strength
- Duo-Pak cartridge dispensing system
- Good adhesion to many plastics and metals

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.


Typical Uncured Physical Properties

Property	Values	Additional Information
Color	Yellow Translucent	View 

Notes: Colors may vary from nearly white to yellow/amber. Adhesive performance is not affected by color variation.

Base Color	Translucent White
------------	-------------------

Accelerator Color	Light Yellow
-------------------	--------------

Base Viscosity	30,000-70,000 cP	View 
----------------	------------------	--

Temp C: 23C
Temp F: 72F

Accelerator Viscosity	30,000-70,000 cP	View 
-----------------------	------------------	--

Temp C: 23C
Temp F: 72F

Base Resin	Modified Epoxy
------------	----------------

Accelerator Resin	Amine
-------------------	-------

Base Net Weight	9.1 to 9.4 lb/gal
-----------------	-------------------


Accelerator Net Weight	9.0 to 9.3 lb/gal
------------------------	-------------------

Mix Ratio by Volume (B:A)	100:100
---------------------------	---------


Mix Ratio by Weight (B:A)	100:99
---------------------------	--------

Typical Mixed Physical Properties


Property	Values	Additional Information
----------	--------	------------------------

Open Time	8 min	View 
-----------	-------	--

Notes: POR=Pop Off Rubber

Worklife	8 to 13 min	View 
----------	-------------	--

Temp C: 23C
Temp F: 73F

Time to Full Cure	0.33 hr	View 
-------------------	---------	--

Temp C: 23C
Temp F: 73F

Notes: The cure time is defined as that time required for the adhesive to achieve a minimum of 80% of the ultimate strength as measured by aluminum-aluminum OLS.

Typical Physical Properties


Property	Values	Additional Information
----------	--------	------------------------

Color	Yellow Translucent	View 
-------	--------------------	--

Test Name: Cured

Typical Cured Characteristics


Property	Values	Additional Information
----------	--------	------------------------

Shore D Hardness	40	View 
------------------	----	--

Test Method: ASTM D2240

Temp C: 23C
Temp F: 73F


Typical Performance Characteristics

Property	Values	Additional Information
Elongation at Break	40 %	
Overlap Shear Strength 48hr Aluminum	2500 lb/in ²	View 

Test Method: ASTM D1002

Test Name: Overlap Shear Strength
Dwell/Cure Time: 48.0
Dwell Time Units: hr
Temp C: 23C
Temp F: 73F
Environmental Condition: Tested at -55C -67F
Substrate: Aluminum


Notes: Overlap shear strength was measured on FPL etched 1in wide x 1/2in overlap specimens. Bonds made with 2 panels of 4in x 7in x 0.063in, 2024 T3 clad AL, cut into 1 in. wide specimens, held with 2psi. Jaw separation 0.1 in/min.

Overlap Shear Strength 48hr Aluminum	2500 lb/in ²	View 
--------------------------------------	-------------------------	--

Test Method: ASTM D1002

Test Name: Overlap Shear Strength
Dwell/Cure Time: 48.0
Dwell Time Units: hr
Temp C: 23C
Temp F: 73F
Substrate: Aluminum


Notes: Overlap shear strength was measured on FPL etched 1in wide x 1/2in overlap specimens. Bonds made with 2 panels of 4in x 7in x 0.063in, 2024 T3 clad AL, cut into 1 in. wide specimens, held with 2psi. Jaw separation 0.1 in/min.

Overlap Shear Strength 48hr Aluminum	270 lb/in ²	View 
--------------------------------------	------------------------	--

Test Method: ASTM D1002

Test Name: Overlap Shear Strength
Dwell/Cure Time: 48.0
Dwell Time Units: hr
Temp C: 23C
Temp F: 73F
Environmental Condition: Tested at 71C 160F
Substrate: Aluminum


Notes: Overlap shear strength was measured on FPL etched 1in wide x 1/2in overlap specimens. Bonds made with 2 panels of 4in x 7in x 0.063in, 2024 T3 clad AL, cut into 1 in. wide specimens, held with 2psi. Jaw separation 0.1 in/min.

Overlap Shear Strength 48hr Aluminum	200 lb/in ²	View 
--------------------------------------	------------------------	--

Test Method: ASTM D1002

Test Name: Overlap Shear Strength
Dwell/Cure Time: 48.0
Dwell Time Units: hr
Temp C: 23C
Temp F: 73F
Environmental Condition: Tested at 82C 180F
Substrate: Aluminum

Notes: Overlap shear strength was measured on FPL etched 1in wide x 1/2in overlap specimens. Bonds made with 2 panels of 4in x 7in x 0.063in, 2024 T3 clad AL, cut into 1 in. wide specimens, held with 2psi. Jaw separation 0.1 in/min.

T-Peel Adhesion 48hr 23C	20 lb/in width	View 
--------------------------	----------------	--

Test Method: ASTM D1876

Test Name: T-Peel Adhesion
Dwell/Cure Time: 48.0
Dwell Time Units: hr
Temp C: 23C


Temp F: 73F

Notes: T-Peel bonds were measured on 1 in. wide specimens cut from two FPL etched 8 in. x 8 in. x .032 in., 2024 T3 clad aluminum panels bonded together. The separation rate of the testing jaws was 20 in/min.

Electrical and Thermal Properties

Property	Values	Additional Information
Glass Transition Temperature (Tg)	13 °C	View 

Notes: Glass Transition Temperature (Tg) determined using DSC Analyzer with a heating rate of 68°F (20°C) per minute. Second heat values given.

Glass Transition Temperature (Tg)	55 °F	View 
-----------------------------------	-------	--

Notes: Glass Transition Temperature (Tg) determined using DSC Analyzer with a heating rate of 68°F (20°C) per minute. Second heat values given.

Volume Resistivity	4.5 x 10 ¹⁰ Ω-cm	View 
--------------------	-----------------------------	--

Test Method: ASTM D257

Temp C: 23C

Temp F: 73F

Coefficient of Thermal Expansion	80 x 10 ⁻⁶	
----------------------------------	-----------------------	--

Coefficient of Thermal Expansion	200 x 10 ⁻⁶	
----------------------------------	------------------------	--

Storage and Shelf Life

Store products at 60-80°F (16-27°C) for maximum storage life.

These products have a shelf life of 24 months in their unopened original containers from date of manufacture.

Bottom Matter

3M

Industrial Adhesives and Tapes Division

3M Center, Building 225-3S-06

St. Paul, MN 55144-1000

800-362-3550

Trademarks

3M and Scotch-Weld are trademarks of 3M Company.

Automotive Disclaimer

Automotive Applications: This product is an industrial product and has not been designed or tested for use in certain automotive applications, including, but not limited to, automotive electric powertrain battery or high voltage applications. This product does not fully adhere to typical automotive design or quality system requirements, such as IATF 16949 or VDA 6.3. This product may not be manufactured in an IATF certified facility and may not meet a Ppk of 1.33 for all properties. The product may not undergo an automotive production part approval process (PPAP). Customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's automotive application and for conducting incoming inspections before use of the product. Failure to do so may result in injury, death, and/or harm to property. No written or verbal statement, report, data or recommendation by 3M related to automotive use of the product shall have any force or effect.

unless in an agreement signed by the Technical Director of 3M's Automotive Division. Customer assumes all responsibility and risk if customer chooses to use this product in an automotive electric powertrain battery or high voltage application, and 3M will not be liable for any loss or damage arising from or related to the 3M product or customer's use of the product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity or recall costs), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability. In no event shall 3M be liable for any damages in excess of the purchase price paid for the product.

NOTWITHSTANDING ANY OTHER STATEMENT TO THE CONTRARY, 3M MAKES NO REPRESENTATIONS, WARRANTIES OR CONDITIONS WHATSOEVER, EXPRESS OR IMPLIED, REGARDING THE PRODUCT IF USED IN AN AUTOMOTIVE ELECTRIC POWERTRAIN BATTERY OR HIGH VOLTAGE APPLICATION, INCLUDING, BUT NOT LIMITED TO, ANY WARRANTY ON PERFORMANCE, LONGEVITY, SUITABILITY, COMPATIBILITY, OR INTEROPERABILITY, OR ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE.

Handling/Application Information

Application Equipment

These products may be applied by spatula, trowel or flow equipment.

Two part mixing/proportioning/dispensing equipment is available for intermittent or production line use. These systems are ideal because of their variable shot size and flow rate characteristics and are adaptable to many applications.

Directions for Use

1. For high strength structural bonds, paint, oxide films, oils, dust, mold release agents and all other surface contaminants must be completely removed from substrates to be bonded. However, the amount of surface preparation necessary directly depends on the user's required bond strength, environmental aging resistance and economic practicalities. For specific surface preparations on common substrates, see the section on surface preparation.

2. These products consist of two parts.

Mixing

For Duo-Pak Cartridges

3M™ Scotch-Weld™ Epoxy Adhesive DP110 Translucent and Gray are supplied in a dual syringe plastic duo-pak cartridge as part of the 3M™ EPX™ Applicator system. To use, simply insert the duo-pak cartridge into the EPX applicator and start the plunger into the cylinders using light pressure on the trigger. Next, remove the duo-pak cartridge cap and expel a small amount of adhesive to be sure both sides of the duo-pak cartridge are flowing evenly and freely. If automatic mixing of Part A and Part B is desired, attach the EPX mixing nozzle to the duo-pak cartridge and begin dispensing the adhesive. For hand mixing, expel the desired amount of adhesive and mix thoroughly. Mix approximately 15 seconds after a uniform color is obtained.

For Bulk Containers

Mix thoroughly by weight or volume in the proportions specified on the product label or in the uncured properties section. Mix approximately 15 seconds after a uniform color is obtained.

3. For maximum bond strength apply product evenly to both surfaces to be joined.

4. Application to the substrates should be made within 8 minutes. Larger quantities and/or higher temperatures will reduce this working time.

5. Join the adhesive coated surfaces and allow to cure at 60°F (16°C) or above until completely firm. Heat up to 200°F (93°C), will speed curing. These products will fully cure in 48 hours @ 75°F (24°C).

6. Keep parts from moving during cure. Contact pressure necessary. Maximum shear strength is obtained with a 3-5 mil bond line.

7. Excess uncured adhesive can be cleaned up with ketone type solvents.*

*Note: When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use.

Adhesive Coverage: A 0.005 in. thick bondline will typically yield a coverage of

320 sqft/gallon.

Surface Preparation

For high strength structural bonds, paint, oxide films, oils, dust, mold release agents and all other surface contaminants must be completely removed from substrate to be bonded. However, the amount of surface preparation necessary directly depends on the user's required bond strength, environmental aging resistance and economic practicalities.

The following cleaning methods are suggested for common surfaces:

Steel:

1. Wipe free of dust with oil-free solvent such as acetone or isopropyl alcohol solvents.*

2. Sandblast or abrade using clean fine grit abrasives.
3. Wipe again with solvent to remove loose particles.*
4. If a primer is used, it should be applied within 4 hours after surface preparation.

Aluminum:

1. Alkaline Degrease: Oakite 164 solution (9-11 oz./gallon water) at 190°F ± 10°F (88°C ± 23°C) for 10-20 minutes. Rinse immediately in large quantities of cold running water.
2. Acid Etch: Place panels in the following solution for 10 minutes at 150°F ± 5°F (66°C ± 23°C).

Sodium Dichromate 4.1 - 4.9 oz./gallon

Sulfuric Acid, 66°Be 38.5 o 41.5 oz./gallon

2024-T3 aluminum (dissolved) 0.2 oz./gallon minimum

Tap water as needed to balance

3. Rinse: Rinse panels in clear running tap water.
4. Dry: Air dry 15 minutes; force dry 10 minutes at 150°F ± 10°F (66°C ± 23°C).
5. If primer is to be used, it should be applied within 4 hours after surface preparation.

Plastics/Rubber:

1. Wipe with isopropyl alcohol.*
2. Abrade using fine grit abrasives.
3. Wipe with isopropyl alcohol.*

*Note: When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use.

References

Property	Values
3m.com Product Page	https://www.3m.com/3M/en_US/p/d/b40066469/
Safety Data Sheet SDS	https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=DP110 Translucent

Family Group

Link Tags:

- DP110 Translucent
- DP110 Gray

Products	Open Time	Color	Worklife	Shore D Hardness
DP110 Gray	8 min	Gray	8 to 13 min	45
DP110 Translucent	8 min	Yellow Translucent	8 to 13 min	40

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Disclaimer: 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit www.3M.com.