



Technical Data Sheet

3M™ Hot Melt Adhesive 3789

Product Description

3M™ Hot Melt Adhesives are heat applied, 100% solids adhesives. 3M™ Hot Melt 3789 is a thermoplastic adhesive to bond to wide variety of substrates such as wood, plastic, vinyl, metal and glass.

• High performance for plastic with good fuel, oil and plasticizer resistance. Long open time.

Product Features

- 100% solids, no VOCs
- Easy to use
- Long open times allow for easy use on large assemblies and large surfaces
- Adhesive sets and obtains strength in seconds
- Creates high performance bonds
- Ideal for woodworking and general industrial applications.

Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

Property	Values	Additional Information
Open Time	50 s	View ^

Substrate: OSB

Notes: Open time is the max time between the application of the adhesive and joining the parts. Data based on 1/8in semicircular bead on non-metallic substrates at 75°F. Higher environmental temperatures and/or larger beads will lengthen open times.

Density	0.95 g/cm³
Density	0.034 lb/in³

Flash Point	>200 °C	View ^
Test Method: ASTM D92-72 Notes: Cleveland Open Cup		
Flash Point	>392 °F	View ^

Test Method: ASTM D92-72

Notes: Cleveland Open Cup



Viscosity	5200 cP	View ^
Notes: Brookfield Thermocel Visc	cometer in Centipoise using a #27 Spindl	e @ 10 RPM.
Delivery Time	70 s	View ^
Notes: Extrusion time for one 1"x	3" PG cartridge.	
UL Listing	UL 94 - V2	
Typical Uncured Physical P	roperties	
Property	Values	Additional Information
Color (solid)	Brown	
Typical Performance Chara	cteristics	
Property	Values	Additional Information
180° Peel Adhesion	256 oz/in	View ^
Substrate: Flexible canvas bonde	d to Douglas Fir	
Application Temperature C	177 to 196 °C	View ^
Notes: Recommended application	n temperature range. Temperature can b	e adjusted to regulate desired viscosity, delivery rate and pot life.
Application Temperature F	350 to 385 °F	View ^
Notes: Recommended application	n temperature range. Temperature can b	e adjusted to regulate desired viscosity, delivery rate and pot life.
Overlap Shear Strength	570 lb/in²	View ^
Substrate: Douglas Fir		
Temperature Resistance	104 °C	View ^
Notes: Highest temperature that	the adhesive will support a 2 psi dead loa	ad
Temperature Resistance	220 °F	View ^
Notes: Highest temperature that	the adhesive will support a 2 psi dead loa	ad
Ball & Ring Melt Point	132 °C	View ^
Test Method: ASTM E28-67		
Ball & Ring Melt Point	270 °F	View ^

EN - July, 2016 2/4 3M™ Hot Melt Adhesive 3789



Test Method: ASTM E28-67

FDA Indirect Food Contact	21 CFR 175.105	View ^
Notes: Permitted for indirect food contact subject to the limitations in applicable CFR section(s).		

Available Sizes

5/8 in x8 in Q 1 in x3 in PG 1/8 in Bulk

Storage and Shelf Life

Store product below 120°F (49°C).

When stored at the recommended conditions, this product has a shelf life of 24 months from date of manufacture.

Industry Specifications

UL 94 - V2

Bottom Matter

3M Industrial Adhesives and Tapes Division 3M Center, Building 225-3S-06 St. Paul, MN 55144-1000 800-362-3550

Trademarks

3M is a trademark of 3M.

Handling/Application Information

Directions for Use

- 1. Surface Preparation: Surfaces must be clean, dry and dust free. Wipe with a solvent such as isopropyl alcohol for plastic, metal and glass substrates to remove oil and dirt.*
- *Note: When using solvents, extinguish all ignition sources, including pilot lights, and follow the manufacturer's precautions and directions for use.
- 2. Application: 3M[™] Hot Melt Adhesives are designed for application with a 3M[™] Hot Melt Applicators. Read and follow the precautions and directions for use in the user's manual before operating the applicator. 3M[™] Hot Melt Adhesives are applied at 350-385°F. Adhesives yield approximately 430 linear feet per pound of adhesive when extruded as a 1/8" diameter semi-circular bead. Extruded bead sizes can be customized using 3M[™] applicator tips.
- 3. Coverage: 3M™ Hot Melt Adhesives yield approximately 430 linear feet per pound of adhesive when extruded as a 1/8" diameter semi-circular bead.
- 4. Set up time: After the bond is made, 3M™ Hot Melt Adhesives immediately build strength and no clamping is necessary. Set will occur faster on cold or metallic substrates.

References

Property	Values
3m.com Product Page	https://www.3m.com/3M/en_US/p/d/b40065547/
Safety Data Sheet SDS	https://www.3m.com/3M/en_US/company-us/SDS-search/results/?

gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=3789

Family Group

Link Tags:

3747

3779

3789

3797

Products	Open Time
3747	N/A
3797	N/A
3789	50 s
3779	N/A

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Disclaimer: 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit www.3M.com.

3M™ Hot Melt Adhesive 3789