

# Technical Data Sheet

## 3M™ PTFE Film Tape 5498

### Product Description

3M™ PTFE Film Tape 5498 has a film backing with a non-silicone rubber adhesive.

### Product Features





- Withstands autoclave cycles for several hours at temperatures up to 350°F (177°C) and 400°F (204°C) exposure for shorter periods.
- Extruded PTFE film tape lies flatter than typical skived PTFE film tapes.

CAUTION: When PTFE film tape is exposed to temperatures above 600°F (316°C), small quantities of hazardous vapors may be released. INHALATION OF THESE VAPORS MAY BE HARMFUL OR MAY CAUSE RESPIRATORY TRACT IRRITATION. Do not heat or expose PTFE film tape to temperatures above 600°F (316°C).

### Technical Information Note










The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

### Typical Physical Properties

Property	Values	Additional Information
Backing	Extruded PTFE (polytetrafluoroethylene)	
Adhesive Type	Rubber	
Color	Brown	
Backing Thickness (mm)	0.06 mm	View 
Test Method: ASTM D3652		
Total Tape Thickness (mil)	4.2 mil	View 
Test Method: ASTM D3652		
Total Tape Thickness (mm)	0.11 mm	View 
Test Method: ASTM D3652		
Backing Thickness	2.2 mil	View 

Test Method: ASTM D3652

## Typical Performance Characteristics

Property	Values	Additional Information
Tensile Strength	33.3 N/cm	<a href="#">View</a> 
Test Method: ASTM D3759		
180° Peel Adhesion	5.1 N/cm	<a href="#">View</a> 
Test Method: ASTM D3330		
Notes: 12 in/min (300 mm/min)		
180° Peel Adhesion	47 oz/in	<a href="#">View</a> 
Test Method: ASTM D3330		
Notes: 12 in/min (300 mm/min)		
Tensile Strength	304 oz/in	<a href="#">View</a> 
Test Method: ASTM D3759		
Elongation at Break (%)	388 %	<a href="#">View</a> 
Test Method: ASTM D3759		
Long Term Temp C	149 °C	<a href="#">View</a> 
Test Condition: Long Term (day, weeks)		
Minimum Long Term Temperature Resistance	4 °C	<a href="#">View</a> 
Test Condition: Long Term (day, weeks)		
Long Term Temp F	300 °F	<a href="#">View</a> 
Test Condition: Long Term (day, weeks)		
Minimum Long Term Temperature Resistance	40 °F	<a href="#">View</a> 
Test Condition: Long Term (day, weeks)		

## Available Sizes

Property	Values	Additional Information
Standard Roll Length	65.8 m	

Standard Roll Length

72 yd

## Storage and Shelf Life

Store under normal conditions of 60° to 80°F (16° to 27°C) and 40 to 60% relative humidity in the original packaging material. To obtain best performance, use this product within 18 months from date of manufacture.

## Bottom Matter

3M  
Industrial Adhesives and Tapes Division  
3M Center, Building 225-3S-06  
St. Paul, MN 55144-1000  
800-362-3550

## Trademarks

3M is a trademark of 3M Company.

## Handling/Application Information

Application Examples

- Lining of composite bonding tool frames where there is concern of silicone contamination.
- Masking and bundling of composite parts prior to bonding operations where there is concern of silicone contamination.

## References

Property	Values
3m.com Product Page	<a href="https://www.3m.com/3M/en_US/p/d/b40070588/">https://www.3m.com/3M/en_US/p/d/b40070588/</a>
Safety Data Sheet SDS	<a href="https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&amp;msdsLocale=en_US&amp;co=ptn&amp;q=5498">https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&amp;msdsLocale=en_US&amp;co=ptn&amp;q=5498</a>

## Family Group

Link Tags:

5498

Products	Backing	Adhesive Type	Color	Total Tape Thickness (mm)	Tensile Strength	Long Term Temp C	Minimum Long	
							Term Temperature Resistance	Long Term Temp F
5498	Extruded PTFE (polytetrafluoroethylene)	Rubber	Brown	0.11 mm	33.3 N/cm	149 °C	4 °C	300 °F

## ISO Statement

This product was manufactured under a quality system registered to ISO 9001 standards.

## Information

**Technical Information:** The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third

party intellectual property rights is granted or implied with this information.

**Product Selection and Use:** Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

**Warranty, Limited Remedy, and Disclaimer:** Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

**Limitation of Liability:** Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

**Disclaimer:** 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit [www.3M.com](http://www.3M.com).